



Technical Data Sheet

Parameters	Standard	Unit	Measurement	
Substance	ISO 536	g/m ²	75	80
Thickness	ISO 534	µm	105	107
Bulk	ISO 534		1,40	1,34
Moisture content	ISO 287	%	4,1	4,3
Roughness	ISO 8791	Bendtsen ml/min	280	230
Whiteness	ISO 11475	CIE	161	161
Brightness	ISO 2470-2	%	108	108
Opacity	ISO 2471	%	92	93



References:

Product is made taking into account requirements of DIN EN 12281
Product made from ECF Pulp

Sylvamo Sweden AB
Nymöllavägen 260-15, 295 73
Nymölla, Sweden
Extract date: May 2023